

FLOORCOTE POLYURETHANE QUICK DRY GLOSS

PRODUCT DESCRIPTION

A range of fast, air drying enamels designed for the coating of concrete floors, suitable for most types of application. Based on a urethane alkyd blend in mixed hydrocarbon solvents.

USES

Floor cote Quick Dry Gloss is a tough, wear resistant film coating which provides ideal floor protection for workshops, showrooms, storage areas and garages. Low slip additives available.

TECHNICAL PROPERTIES

Colour	5 Standard Colours
Finish	Gloss
Curing Agent	N/A
Mix Ratio	N/A
Specific Gravity	0.98
Volume Solids	45%
Recommended Film Thickness	90mm WFT / 40mm DFT
Theoretical Spreading Rate	11 m ² /litre
Application Method	Brush, Roller
Flash Point	28°C
VOC	435 g/litre

Drying Times

	10°C	20°C	30°C
Touch Dry	4 hours	2 hour	1½ hours
Hard Dry	24 hours	14 hours	10 hours
Minimum Overcoat	36 hours	24 hours	18 hours
Maximum Overcoat	Indefinite	Indefinite	Indefinite

N.B. On floors subject to vehicle traffic, a minimum of 48 hours should be allowed before overcoating..

RECOMMENDED SYSTEMS

Floorcote Epoxy Sealer, Floorcote Etch Treatment, Floorcote Degreaser

Paco systems
Broadridge Close
Newton Abbot
Devon TQ12 1YE

Tel: 01626 207064
Fax: 08712 424345
www.paco-systems.co.uk
info@paco-systems.co.uk

*Paints and Coatings
for Industry*

SURFACE PREPARATION

Ensure surfaces are clean, dry and free from dirt, grease and other contamination. On new aged concrete, thin first coat 10% with White Spirit. New concrete should be left at least 3 months before painting, then a moisture check carried out to ensure this lies within acceptable limits. On previously painted surfaces, test a small area before full painting. Damp surfaces can be coated with Floorcote Epoxy Sealer before applying paint. Hard concrete or granolithic surfaces should be 'opened' with Floorcote Etch treatment. Floorcote Degreaser is recommended for heavy dirt and grease contamination.

PRODUCT APPLICATION

Mixing Mix thoroughly before use.

Thinners White Spirit

Brush Thin first coat 10% White Spirit and work well into surface. Apply a second full coat. If previously sealed with Floorcote Epoxy Sealer, apply two full coats. On previously painted surfaces, one full coat is usually sufficient to give full cover and even-ness.

Roller Thin first coat 10% White Spirit and work well into surface. Apply a second full coat. If previously sealed with Floorcote Epoxy Sealer, apply two full coats. On previously painted surfaces, one full coat is usually sufficient to give full cover and even-ness.

Cleaner White Spirit

Cleanup Considerations All equipment should be cleaned immediately after use with White Spirit. It is advisable that equipment should be cleaned/flushed during the course of application, the frequency of which will depend on the volume of material used and timescale over which applied. Ensure all waste materials (including packaging) are disposed of in accordance with local regulations.

HEALTH, SAFETY & ENVIRONMENTAL

This product must be used in accordance with the Material Safety Data Sheet supplied by the manufacturer. The user must observe local health, safety and environmental regulations when using this product. Consult the manufacturer if there are any concerns over the suitability of this product.

PACK SIZES

5 litre

PACK WEIGHTS

5 litre: 5.30 Kg.

Paco systems

Broadridge Close
Newton Abbot
Devon TQ12 1YE

Tel: 01626 207064

Fax: 08712 424345

www.paco-systems.co.uk

info@paco-systems.co.uk

*Paints and Coatings
for Industry*



SPECIALIST PAINTS FOR INDUSTRY

STORAGE CONDITIONS

Store away from extremes of temperature.

LIMITATIONS

Do not apply below 5°C as drying may be affected. Ensure adequate ventilation and drying conditions prevail. Over-thick application should be avoided, this will extend the drying period.

DISCLAIMER

The information given in these specifications and technical advice - whether verbal, in writing or by way of trials is for guidance and is given in good faith, but without warranty. This also applies where propriety rights or third parties are involved. Any person using these products without first making further enquiries as to the suitability of the products for the intended purpose and testing the products to assess their fitness for the purpose does so at their own risk. The application, use and processing of the products are beyond our control and are therefore your own responsibility, and we can accept no liability for the performance of the products arising out of such use, beyond the value of the goods delivered by us. The information contained in these data sheets is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to ensure that this sheet is current prior to using the product.

Paco systems
Broadridge Close
Newton Abbot
Devon TQ12 1YE

Tel: 01626 207064
Fax: 08712 424345
www.paco-systems.co.uk
info@paco-systems.co.uk

*Paints and Coatings
for Industry*