

HR Aluminium.

TECHNICAL DATA	
STANDARD COLOURS	Aluminium.
DRY FILM APPEARANCE	Satin Smooth.
SPREADING RATE	15 to 17 m ² p/lit.
TOUCH DRY @ 20°C	1 Hour.
RECOATING TIME @ 20°C	4 Hours.
AVERAGE WET FILM THICKNESS	90 Microns
AVERAGE DRY FILM THICKNESS	40 Microns .
SOLIDS by VOLUME.	43%
VOLATILE ORGANIC COMPOUNDS.	480 Gms/Lt.
APPLICATION METHODS .	Brush, Roller or Spray
SUBSTRATES	Suitably cleaned and dry surfaces
THINNERS & TOOL CLEANING.	Thinners type KPT04
FLASH POINT.	Above 32°C
PACK SIZES.	5lt, 20lt, 25lt & 205lt,
SHELF LIFE.	12 Months.
MIN' APPLICATION TEMPERATURE	7°C

PRODUCT FEATURES,

- * Heat resisting to 220°C
- * Easy to use product
- * Tough Surface Finish
- * Resists Corrosion

DESCRIPTION & RECOMMENDED USES

This product is formulated on a modified alkyd resin to provide a durable aluminium finish. This is a versatile material widely used on Machinery, Containers, Tanks & Pipe work, Agricultural Plant & Equipment etc.

APPLICATION

Stir well prior to use. The paint is best applied by Brush or Roller, although after thinning it can be applied by spray. Surfaces should be free from surface contamination such as grease, oil, loose or flaking paint.

All tools and equipment should be cleaned immediately after use thinners, type KPT04.

HEALTH and SAFETY See separate Health and Safety sheet.

The manufacturer follows a process of continuous improvement, which may lead to specification changes, also the actual application method and substrate are beyond our control. This Data Sheet is issued for general guidance only. It is based on tests and information believed to be correct at the time of printing. All recommendations issued by or on behalf of the company are subject to the company's conditions of sale.

Paco systems
Broadridge Close
Newton Abbot
Devon TQ12 1YE

Tel: 01626 207064
Fax: 08712 424345
www.paco-systems.co.uk
info@paco-systems.co.uk

*Paints and Coatings
for Industry*