

## Polyurethane Floor Paint Anti Slip

### STANDARD COLOURS:

Venetian Red 04C39, Mid Grey 18B25, Light Grey 18B21, Brunswick Green 14C39, Light Green 14C37, Cream 06C33, Black 00E53 and Blue 18E53.

### DRY FILM APPEARANCE

Satin Smooth.

### SPREADING RATE

10 to 15 m<sup>2</sup> p/lit.

### TOUCH DRY @ 20°C

4 Hours.

### RECOATING TIME @ 20°C

Over night.

### AVERAGE WET FILM THICKNESS

75 to 100 Microns.

### AVERAGE DRY FILM THICKNESS

32 to 43 Microns.

### SOLIDS by VOLUME.

48%

### VOLATILE ORGANIC COMPOUNDS.

480 gms/Lt.

### APPLICATION METHODS.

Brush, Roller or Spray.

### SUBSTRATES.

Suitably cleaned and dry surfaces.

### THINNERS & TOOL CLEANING.

Thinners type KPT04.

### FLASH POINT.

Above 320°C

### PACK SIZES.

5lt, 20lt & 205lt.

### SHELF LIFE.

12 Months.

### MIN' APPLICATION TEMPERATURE.

7°C

### PRODUCT FEATURES:

\* Tough Surface Finish

\* Easy to Use

\* Fast Roller Application

\* Attractive Colours

**DESCRIPTION & RECOMMENDED USES;** This product is a good quality general purpose floor paint formulated on high quality polyurethane reinforced resins to provide a tough surface finish suitable for, Factories, Garages, Warehouses, Offices, Show Rooms, Workshops etc. On curing it provides a tough and durable textured finish with good anti-slip properties.

**APPLICATION;** Stir well prior to use. The paint is best applied by Brush or Roller although after thinning it can be applied by Spray. Surfaces should be clean and free from surface contamination such as grease, oil, loose or flaking paint, with a moisture content of less than 7%.. Previously unpainted concrete floors are best treated with two coats, the first thinned with 10-15% thinners KPT04 to act as a sealer coat, and the second coat unthinned. All tools and equipment should be cleaned immediately after use with thinners type KPT04.

## HOW TO APPLY:

1. Sweep up Loose Debris.
2. Ensure floor is free from oil & grease.
3. If the floor is Power Floated or has a Grano Finish apply Concrete Floor Etch as directed on the relevant Technical Data Sheet. (Floors that are treated with a chemical hardener may not be suitable for painting, if you are unsure test a small area prior to painting.)
4. Paint by hand round wall edges, pillars machinery etc.
5. Thin the first coat of floor paint with 10% thinners and apply to floor, leave to dry overnight with adequate ventilation.
6. Apply second coat of floor paint full strength leave to dry overnight with adequate ventilation.
7. Floor is ready for use after 12 hours with adequate ventilation.
8. It is ALWAYS better to apply two thin coats rather than one thick coat.

**HEALTH and SAFETY;** See separate Health and Safety sheet.