

## 2 PACK YELLOW ETCH PRIMER (N4700-2-1)

### PRODUCT DESCRIPTION

An air drying anticorrosive etching primer based on a modified vinyl resin designed to promote adhesion to metallic substrates.

---

### USES

As an effective adhesion promoter for ferrous and non ferrous substrates, particularly aluminium. Product can be overcoated with a range of finishes.

---

### TECHNICAL PROPERTIES

<b>Colour</b>	Yellow		
<b>Finish</b>	Matt, Translucent		
<b>Curing Agent</b>	2 Pack Etch Primer Activator (N1000-1-1)		
<b>Mix Ratio</b>	1:1 by volume		
<b>Specific Gravity</b>	0.874		
<b>Volume Solids</b>	8 ± 2%		
<b>Recommended Film Thickness</b>	60-100µ WFT / 5-8µ DFT		
<b>Theoretical Spreading Rate</b>	10-16 m <sup>2</sup> /litre		
<b>Application Method</b>	Spray only		
<b>Flash Point</b>	Base 10°C Activator 24°C		
<b>VOC</b>	755 g/litre		
<b>Drying Times</b>	<b>10°C</b>	<b>20°C</b>	<b>30°C</b>
Touch Dry	10-20 minutes	5-10 minutes	3-5 minutes
Hard Dry	20-30 minutes	10-20 minutes	5-10 minutes
Minimum Overcoat*	20 minutes	10 minutes	5 minutes
Maximum Overcoat	Indefinite	Indefinite	Indefinite

\*Overcoating can take place as soon as product is touch dry.

---

### CERTIFICATION/APPROVALS

---

#### RECOMMENDED SYSTEMS

Most of Spencer's air drying single and 2 pack finishes.

---

#### SURFACE PREPARATION

Surfaces to be painted should be clean, dry and free of any corrosion, oil or grease. Corrosion resistance will be enhanced by use of a suitable phosphate pre-treatment.

---

**Paco systems**  
Broadridge Close  
Newton Abbot  
Devon TQ12 1YE

Tel: 01626 207064  
Fax: 08712 424345  
[www.paco-systems.co.uk](http://www.paco-systems.co.uk)  
[info@paco-systems.co.uk](mailto:info@paco-systems.co.uk)

Paints and Coatings  
for Industry

**PRODUCT APPLICATION**

<b>Mixing</b>	Mix 1 part base : 1 part activator by volume. Stand for 20 minutes before use. Pot life 8 hours, do not mix more than required.
<b>Thinners</b>	Do not thin. Ready to use.
<b>Conventional Spray</b>	<u>Gravity Fed Gun</u> 1.2 – 1.4 mm nozzle Pressure 3.0 – 3.5 Bar <u>Suction Fed Gun</u> 1.4 – 1.6 mm nozzle Pressure 4.0 – 5.0 Bar
<b>HVLP Spray</b>	<u>Gravity Fed Gun</u> 1.1 – 1.3 mm nozzle Pressure 0.3 – 0.7 Bar <u>Suction Fed Gun</u> 1.2 – 1.3 mm nozzle Pressure 0.3 – 0.6 Bar
<b>Cleaner</b>	Thinner No.5
<b>Cleanup Considerations</b>	All equipment should be cleaned immediately after use with Thinner No.5 It is advisable that equipment should be cleaned/flushed during the course of application, the frequency of which will depend on the volume of material used and timescale over which applied. Ensure all waste materials (including packaging) are disposed of in accordance with local regulations.

---

**HEALTH, SAFETY & ENVIRONMENTAL**

This product must be used in accordance with the Material Safety Data Sheet supplied by Spencer Coatings Limited.  
The user must observe local health, safety and environmental regulations when using this product.  
Consult if there are any concerns over the suitability of this product.

---

**Paco systems**  
Broadridge Close  
Newton Abbot  
Devon TQ12 1YE

Tel: 01626 207064  
Fax: 08712 424345  
[www.paco-systems.co.uk](http://www.paco-systems.co.uk)  
[info@paco-systems.co.uk](mailto:info@paco-systems.co.uk)

*Paints and Coatings  
for Industry*

---

**PACK SIZES**

5 litre Base, 5 litre Activator

---

**PACK WEIGHTS**

5 litre Base : 4.52 Kg. 5 litre Activator : 4.22 Kg.

---

**STORAGE CONDITIONS**

Store away from extremes of temperature and direct heat. If kept in suitable storage, a shelf life of 6 months should be expected.

---

**LIMITATIONS**

Application of excessive film thicknesses will detract from final product properties. Low temperatures and/or high humidity will retard the drying time. Spray only in warm, dry conditions.

---

**DISCLAIMER**

The information given in these specifications and technical advice - whether verbal, or in writing or by way of trials is for guidance only and is given in good faith, but without warranty. This also applies where proprietary rights or third parties are involved. Any person using products without first making further enquiries as to the suitability of the products for the intended purpose and testing the products to assess their fitness for the purpose does so at their own risk. The application, use and processing of the products are beyond our control and are therefore your own responsibility, and we can accept no liability for the performance of the products arising out of such use, beyond the value of the goods delivered by us. The information contained in these data sheets is liable to modification from time to time in the light of experience and our policy of continuous development.

It is the user's responsibility to ensure that this sheet is current prior to using the product.

**Paco systems**  
Broadridge Close  
Newton Abbot  
Devon TQ12 1YE

Tel: 01626 207064  
Fax: 08712 424345  
[www.paco-systems.co.uk](http://www.paco-systems.co.uk)  
[info@paco-systems.co.uk](mailto:info@paco-systems.co.uk)

*Paints and Coatings  
for Industry*