

SPEEDCOAT MD90 COMPLIANT COATING

PRODUCT DESCRIPTION

A specially formulated single application high build compliant coating based on a fast drying high solid alkyd resin. The product has excellent chip resistance, corrosion and seawater resistance, verified by salt spray and humidity evaluations.

USES

Direct primerless coating for containers, machinery and general steel fabrications used in marine, industrial and other aggressive environments. Product used if a high gloss version of Speedcoat MD60 Compliant Coating is required.

TECHNICAL PROPERTIES

Colour	RAL, BS 4800, Special Colours		
Finish	Full Gloss		
Curing Agent	n/a		
Mix Ratio	n/a		
Specific Gravity	1.30		
Volume Solids	53 ± 2%		
Recommended Film Thickness	188 – 264µm WFT / 100 -140µm DFT		
Theoretical Spreading Rate	3.8– 5.3 m ² /litre		
Application Method	Spray, small touch up areas can be brushed		
Flash Point	28°C		
VOC	415 g/litre		

Drying Times	10°C	20°C	30°C
Touch Dry	1 hours	1 hour	40 minutes
Hard Dry	5 hours	2 ½ hours	2 hours
Minimum Overcoat	-	-	-
Maximum Overcoat	-	-	-

CERTIFICATION/APPROVALS

RECOMMENDED SYSTEMS

Not recommended with other products.

SURFACE PREPARATION

Ensure surfaces are clean, dry and free from dirt, grease and other contamination.

Remove scale and rust and prepare to a minimum ST3.

Apply two coats by applying initially 100 micron wet followed by a brief dry off period then a further application of up to 200 micron.

Allow to dry for approx. 3 hours before handling.

Paco systems
Broadridge Close
Newton Abbot
Devon TQ12 1YE

Tel: 01626 207064
Fax: 08712 424345
www.paco-systems.co.uk
info@paco-systems.co.uk

*Paints and Coatings
for Industry*

PRODUCT APPLICATION

Mixing	Stir thoroughly before use.
Thinners	Do not thin.
Brush	Small touch up areas only.
Roller	Small touch up areas only.
Conventional Spray	Not recommended.
Airless Spray	Do not thin. Use tip 0.38-0.53 mm, 50-65° angle and 2000-2300 psi pressure.
Air Assisted Airless Spray	Do not thin. Use 800-1000 psi pressure and 1.4-1.8 mm diameter nozzle.
Cleaner	Thinner No.4
Cleanup Considerations	All equipment should be cleaned immediately after use with Thinner No.4 It is advisable that equipment should be cleaned/flushed during the course of application, the frequency of which will depend on the volume of material used and timescale over which applied. Ensure all waste materials (including packaging) are disposed of in accordance with local regulations.

HEALTH, SAFETY & ENVIRONMENTAL

This product must be used in accordance with the Material Safety Data Sheet supplied by Spencer Coatings Limited.
The user must observe local health, safety and environmental regulations when using this product.
Consult if there are any concerns over the suitability of this product.

PACK SIZES

5 and 20 litre

PACK WEIGHTS

5 litre: 6.5 Kg.
20 litre: 26 Kg.

STORAGE CONDITIONS

Store away from extremes of temperature.

LIMITATIONS

Do not apply when RH exceeds 88% or the surface is less than 2°C above dew point.

INCORRECT APPLICATION (SUCH AS EXCESSIVE FILMS) CAN LEAD TO IMMEDIATE AND LONG TERM FILM DEFECTS.

Paco systems
Broadridge Close
Newton Abbot
Devon TQ12 1YE

Tel: 01626 207064
Fax: 08712 424345
www.paco-systems.co.uk
info@paco-systems.co.uk

*Paints and Coatings
for Industry*

DISCLAIMER

The information given in these specifications and technical advice - whether verbal, or in writing or by way of trials is for guidance only and is given in good faith, but without warranty. This also applies where proprietary rights or third parties are involved. Any person using products without first making further enquiries as to the suitability of the products for the intended purpose and testing the products to assess their fitness for the purpose does so at their own risk. The application, use and processing of the products are beyond our control and are therefore your own responsibility, and we can accept no liability for the performance of the products arising out of such use, beyond the value of the goods delivered by us. The information contained in these data sheets is liable to modification from time to time in the light of experience and our policy of continuous development.

It is the user's responsibility to ensure that this sheet is current prior to using the product.

Paco systems
Broadridge Close
Newton Abbot
Devon TQ12 1YE

Tel: 01626 207064
Fax: 08712 424345
www.paco-systems.co.uk
info@paco-systems.co.uk

*Paints and Coatings
for Industry*